

	L #	Hits	Search Text	DBs
1	L1	361	solventless near3 epoxy	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
2	L2	78	1 and (glass adj (fiber filament strand))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
3	L3	17	2 and hardener	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
4	L4	12	3 and epichlorohydrin	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
5	L5	12	4 and bisphenol	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
6	L6	12	5 and (cure cured curing)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
7	L7	68	2 and (coat\$4 size sized sizing)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
8	L8	30	7 and epichlorohydrin	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
9	L9	28	8 and bisphenol	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
10	L10	27	9 and (reaction adj product)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
11	L11	11	10 and hardener	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB